



# Decorative Vinyl & Fabric Corp.

## Spec Sheet:

### Urban Exotics

<http://dvcfabric.com/vinyl/product/crock/>

#### Technical Specs

|                     | <u>Values</u>                | <u>Test Method</u> |
|---------------------|------------------------------|--------------------|
| Surface Composition | PVC                          |                    |
| Finished Width      | 54" min.                     | ASTM D 751-06      |
| Weight at 54 inches | 33 oz./yd                    | ASTM D 751-06      |
| Thickness           | 1.0 mm ±10%                  | ASTM D 751-06      |
| Total Weight        | 22 oz./yd <sup>2</sup> ±10%  | ASTM D 751-06      |
| Backing Composition | 65% Polyester / 35% Cotton   | ASTM D 751-06      |
| Backing Weight      | 3.5 oz / sq. yd <sup>2</sup> | ASTM D 751-06      |
| Repeat              | V: 10" / H: 10.75"           | ASTM D 751-06      |
| Railroaded          | No                           |                    |
| Put-up              | 30 yards                     |                    |
| Cleaning Code       | W                            |                    |

#### Performance

|                    | <u>Values</u>                        | <u>Test Method</u>   |
|--------------------|--------------------------------------|----------------------|
| Grab Tensile       | 85 lbs./in. × 90 lbs./in. min.       | ASTM D 751-06        |
| Trap Tear          | 15 lbs./in. × 15lbs./in. min.        | ASTM D 751-06        |
| Seam Strength      | 65 lbs./in. × 65 lbs./in. min.       | ASTM D 751-06        |
| Adhesion           | 4 lbs./in. × 4 lbs./in. min.         | ASTM D 751-06        |
| Flex Resistance    | 25,000 Cycles                        | ASTM D 2097-03(2010) |
| Blocking           | No. 1 - Pass                         | FTMS 191A-TM5872     |
| Wyzenbeek Abrasion | Pass - 35,000 cycles, #8 cotton duck | ASTM D 4157-92       |
| UV Stability       | 40 hours (no color change)           | ASTM D 4329-05       |
| Crock Resistance   | 20 cycles - Pass                     | AATCC 8-2007         |
| Stretch (MD×CD)    | 2.2% × 9% at 15 lbs.                 | ASTM D 751-06        |

#### Flamability

|                                     |      |
|-------------------------------------|------|
| California Bulletin 117, Section E. | Pass |
| U.F.A.C. Class I                    | Pass |
| NFPA 260                            | Pass |

#### Suitable Applications: Residential

Country of Origin: China

02/20/2006 - Revision: 1