

PRODUCT SPECIFICATION AZTEC

Surface Type:	100%PVC		Date: 9/20/06
Weight at 54 inches:	28.5oz/yd		Revision: 2
Backing weight:	4oz/yd ²		
Backing Type/composition:	P/C: 65%:35%		
Put-up:	30 yards		
Repeat:	12 1/2" V; 9 1/2" H		
Finish:	Urethane Top Coat		
Cleaning Code:	W		
Railroaded:	N		
Available Test	Values Required	Units	Test Method
Finished Width	54"	In	CFFA-700a
Thickness	1.0±10%	mm	CFFA-700c
Total Weight	19.0+10%	Oz/yd ²	CFFA-700d
Grab Tensile	80.0×80.0min	Lbs/in	CFFA-17
Trap Tear	18.0×18.0min	Lbs/in	CFFA-16c
Seam Strength	75.0×65.0min	Lbs/in	CFFA-14
Adhesion	4.0×4.0min	Lbs/in	CFFA-3
Flex Resistance	25,000	Cycles	CFFA-10
Blocking	No.1	Grade	CFFA-4
Wyzenbeek Abrasion	Pass - 35,000	Cycles	Federal Standard 191A Method 5304
		#8 Cotton Duck	
UV Stability	40 indoor hours	No colour change	QUV
Crock Resistance	20 - no stain	Cycles	CFFA-7
Stretch (MD×CD)	2%×7%	% at 15#	CFFA-17
Flame Resistance:			
California Technical Bulletin 117, Section E.		Meets Requirements	
U.F.A.C. Class I		Meets Requirements	
NFPA 260		Meets Requirements	
May Comply with California 133 when Tested with Suitable Components.			
Country of Origin: China			