

## PRODUCT SPECIFICATION CASCADE

Surface Type:	100% PVC		Date: 4/23/09
Weight at 54 inches:	33oz/yd		Revision: 0
Backing weight:	3.5oz/yd <sup>2</sup>		
Backing Type/composition:	P/C: 65%:35%		
Put-up:	40 yards		
Repeat:	None		
Finish:	PVC Finish		
Cleaning Code:	W		
Railroaded:	N		
<b>Available Test</b>	<b>Values Required</b>	<b>Units</b>	<b>Test Method</b>
Finished Width	54" min	In	CFFA-700a
Thickness	1.0±10%	mm	CFFA-700c
Total Weight	22±10%	Oz/yd <sup>2</sup>	CFFA-700d
Grab Tensile	85×90min	Lbs/in	CFFA-17
Trap Tear	15×15min	Lbs/in	CFFA-16c
Seam Strength	65×65min	Lbs/in	CFFA-14
Adhesion	4×4min	Lbs/in	CFFA-3
Flex Resistance	25,000	Cycles	CFFA-10
Blocking	No.1	Pass	CFFA-4
Wyzenbeek Abrasion	Pass - 35,000	Cycles #8 Cotton Duck	Federal Standard 191A Method 5304
Hydrolysis Resistance	No delaminating	Visual	6 hours boiling water
UV Stability	40 indoor hours	No colour change	QUV
Crock Resistance	20 - no stain	Cycles	CFFA-7
Stretch (MD×CD)	2.2×9	% at 15#	CFFA-17
<b>Flame Resistance:</b>			
California Technical Bulletin 117, Section E.		Meets Requirements	
U.F.A.C. Class I		Meets Requirements	
NFPA 260		Meets Requirements	
May comply with California 133 when tested with suitable components.			
<b>Country of Origin: China</b>			