PRODUCT SPECIFICATION
GUNSMOKE & SPA

Surface Type:	100% PU		Date: 06/20/05
Foam Type:	100% PVC		Revision: 0
Weight at 54 inches:	24oz/yd		
Backing weight:	3.5oz/yd2		
Backing Type/composition:	P/C: 65%:35%		
Put-up:	30-50 yards		
Finish:	Urethane Finish		
Cleaning Code:	W		
Railroaded:	N		
Available Test	**Values Required**	**Units**	**Test Method**
Finished Width	54″	In	CFFA-700a
Thickness	1.0±10%	mm	CFFA-700c
Total Weight	16.0+10%	Oz/yd2	CFFA-700d
Grab Tensile	80×90min	Lbs/in	CFFA-17
Trap Tear	25.0×20min	Lbs/in	CFFA-16c
Seam Strength	65×60min	Lbs/in	CFFA-14
Adhesion	4×4min	Lbs/in	CFFA-3
Flex Resistance	25,000	Cycles	CFFA-10
Blocking	No.1	Pass	CFFA-4
Wyzenbeek Abrasion	Pass - 100,000	Cycles #8 Cotton Duck	Federal Standard 191A Method 5304
Hydrolysis Resistance	No delaminating	Visual	6 hours boiling water
UV Stability	40 indoor hours	No colour change	QUV
Crock Resistance	20 - no stain	Cycles	CFFA-7
Stretch (MD×CD)	5%×15%	% at 15#	CFFA-17
Flame Resistance:			
California Technical Bulletin 117, Section E.		Meets Requirements	
U.F.A.C. Class I		Meets Requirements	
NFPA 260		Meets Requirements	
May comply with California 133 when tested with suitable components.			
Country of Origin: China			