

PRODUCT SPECIFICATION JAGUAR

Surface Type:	100% PU		Date: 4/10/08
Weight at 54 inches:	16.5oz/yd		Revision: 0
Backing weight:	4.5oz/yd ²		
Backing Type/composition:	100% Polyester		
Put-up:	30-50 yards		
Repeat:	None		
Finish:	Urethane Top Coat		
Cleaning Code:	W		
Railroaded:	N		
Available Test	Values Required	Units	Test Method
Finished Width	54"	In	CFFA-700a
Thickness	1.0 ±10%	mm	CFFA-700c
Total Weight	11 ±10%	Oz/yd ²	CFFA-700d
Grab Tensile	100.0×100.0min	Lbs/in	CFFA-17
Trap Tear	18×18.0min	Lbs/in	CFFA-16c
Seam Strength	40.0×07.0min	Lbs/in	CFFA-14
Adhesion	4.0×4.0min	Lbs/in	CFFA-3
Flex Resistance	25,000	Cycles	CFFA-10
Blocking	No.1	Grade	CFFA-4
Wyzenbeek Abrasion	Pass - 100,000	Cycles	Federal Standard 191A Method 5304
		Wire Screen	
UV Stability	40 indoor hours	No colour change	QUV
Crock Resistance	20 - no stain	Cycles	CFFA-7
Stretch (MD×CD)	10%×30%	% at 15#	CFFA-17
Flame Resistance:			
California Technical Bulletin 117, Section E.		Meets Requirements	
U.F.A.C. Class I		Meets Requirements	
NFPA 260		Meets Requirements	
FMVSS-302		Meets Requirements	
May comply with California 133 when tested with suitable components.			
Country of Origin: China			