

PRODUCT SPECIFICATION LIZARDO

Surface Type:	100% PU		Date: 09/20/06
Weight at 54inches:	18.8oz/yd		Revision: 1
Backing weight:	4oz/yd ²		
Backing Type/composition:	P/C: 65%:35%		
Put-up:	30-50 yards		
Repeat:	9" V, 8" H		
Cleaning Code:	W		
Railroaded:	N		
Available Test	Values Required	Units	Test Method
Finished Width	54"	In	CFFA-700a
Thickness	1.0±10%	mm	CFFA-700c
Total Weight	12.5±10%	Oz/yd ²	CFFA-700d
Grab Tensile	80.0×90.0min	Lbs/in	CFFA-17
Trap Tear	15.0×12.0min	Lbs/in	CFFA-16c
Seam Strength	60×60.0min	Lbs/in	CFFA-14
Adhesion	4.0×4.0min	Lbs/in	CFFA-3
Flex Resistance	25,000	Cycles	CFFA-10
Blocking	No.1	Pass	CFFA-4
Wyzenbeek Abrasion	Pass - 100,000	Cycles	Federal Standard 191A Method 5304
		Wire Screen	
Hydrolysis Resistance	No delaminating	Visual	6hrs in boiling water
UV Stability	40 indoor hours	No colour change	QUV
Crock Resistance	20 - no stain	Cycles	CFFA-7
Stretch(MD×CD)	2%×12%	% at 15#	CFFA-17
Flame Resistance:			
California Technical Bulletin 117, Section E.		Meets Requirements	
U.F.A.C. Class I		Meets Requirements	
NFPA 260		Meets Requirements	
May comply with California 133 when tested with suitable components.			
Country of Origin: China			