

Turner

SPECIFICATIONS

Description	Turner 1009 Plum
Abrasion	Exceeds 500,000 Double Rubs.
Backing Content	30% Cotton 70% Polyester
Cleaning Instruction	See Features/Cautions.
Cold Crack	Product Cold Crack is equal to or greater than -40 degrees Celsius (-40 Fahrenheit)
Colors Available	26 colors available.
Construction	Vinyl
Content	100% Polyurethane (PU)
Description	Simulated Leather Vinyl, Contract Rated
Eco Friendly	Eco-Friendly
Elongation	ASTM D5034: Warp: 23.4%, Fill: 38.1 %
Features	Wipe with a soft cloth, with cold water and a mild soap. Dry immediately. Hydrolysis pass 3 weeks (equal 3 years) Phthalate Free PVC Free
Fire Retardancy	California Bulletin 117-Section E, Motor Vehicle Safety Standard 302. NFPA 260 Class 1. UFAC Class 1
Roll Size	30 yards (27.4 m)
Style	Solids / Plain
Tear Strength	Passes ASTM D2261 - Warp = 20 lbs and Fill = 12 lbs.
Tensile Strength	Passes ASTM D5034 - Warp = 105 lbs and Fill = 74 lbs.
Ultraviolet	Colorfastness to Light AATCC16 Class 4.5
Uses	Upholstery
Weight	14.12 ounces per square yard. 21.18 Ounces per Linear Yard
Width	54" (137 cm)

** This information is offered for your general guidance only. It is accurate to the best of our knowledge and is not intended to relieve the user from its responsibility to investigate and understand other pertinent sources of information and to comply with all laws and procedures applicable to the safe handling and use of this material. Final determination of the suitability of any product for an application rests with the user.

*This term and any corresponding data refer to typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Although we do our best to make sure that the colors on our web site are accurate, actual colors will vary. Subtle color differences and textures may not be fully appreciated on some systems due to differences in monitors and/or printers.