



**Decorative Vinyl
& Fabric Corp.**
Symphony Encore
<http://dvcfabric.com>

4527 GLENWOOD ROAD
BROOKLYN, NY 11203
P: 718 941 3326
F: 718 941 6115
E: sol@dvcfabric.com
Product Specification Sheet

Pattern: Element

Date: 4/2/2014

Encore by The Symphony Collection

Description

General Treatments

Weight (linear yard)	18.0 oz	Hydrolysis Resistance	7 weeks	ISO1419:1995 (Jungle Test)
Width	54 "	Colorfastness to Light	1400 Hours	(CFFA-2 / QUV CFFA2/Xenon-ARC)
Thickness	0.80 mm	Cold Crack	-20 °F	(CFFA-6a Federal Standard No. 191A-Method 5874)
Gauge	32 g	Mildew Resistant	Pass	(CFFA-120 / ASTM G21-96)
Emboss	Paper	Anti-Bacterial / Anti-Microbial	Pass	(CFFA-300 / AATCC* Test Method 147-1998)
Surface Composition	100 % Polyurethane	Bleach Resistant	Yes	Diluted 3:1
Substrate Composition	100 % Polyester Knit			

Physical Properties

Abrasion	1,000,000 Double Rubs	(CFFA-1A / Method ASTM D 4157-92)
Tear Strength - Tongue	10.2 Warp 13.2 Fill	(CFFA 16 / ASTM D751-00)
Breaking Strength	10.3 Warp 16.2 Fill	(CFFA-17 / ASTM D2261-00)
Croaking	5 Dry 5 Wet	AATCC-Method 8-2001
Colorfastness to Perspiration	5 Rating	AATCC 15-2007
Colorfastness to Ozone	5 Rating	AATCC 109
Colorfastness to Sea Water	5 Rating	AATCC 106-2007
Colorfastness to Chlorinated Water	5 Rating	AATCC 162-2002
Colorfastness to Gas	4.5 Rating	AATCC 23

Flame Treatments

California Technical Bulletin 117	Pass	NFPA 260	Pass
UFAC Class I	Pass	IMO A.652(16)8.2	Pass
BIFMA CS-191-53, Section 3	Pass		
BIFMA CS-191-53, Section 4	Pass		