

Lucerne

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD) 18.05 oz per linear yard

WIDTH 54"

COMPOSITION 93% Polyester / 4% Polyurethane / 3% Silicone

☐ PIFCF DYFD ☐ YARN DYFD ■ FIBER DYFD ☐ JACQUARD DOBBY ☐ PILE

YARN PER INCH 83.3 EPI, 45.7 PPI

YARN SIZE 1250D+300DD Warp, 1250D Fill

BACKING Polyurethane

CLEANING CODE SW, Spot clean with upholstery shampoo, foam from a mild detergent, or a mild dry cleaning solvent. Do not saturate with liquid. Pile fabrics may require brushing to restore appearance. Cushion cover should not

be removed and dry cleaned.

BC, Lightly spray with a 10% dilution of Household Bleach and water. After the appropriate contact time, blot surface dry and

wipe or rinse with fresh water and blot dry.

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE 100,000+ Double Rubs* ASTM D4157-13 HYDROSTATIC PRESSURE (SUTER) 270+cm (maximum) AATCC 127-13, Option 1 **BREAKING STRENGTH** 290 Warp, 192 Fill ASTM D5034-09 **BRUSH PILL** Class 5 **ASTM D3511 CROCKING RESISTANCE** 5 Dry, 5 Wet **AATCC 8-2016** COLORFASTNESS TO LIGHT Class 5, 40 hours AATCC 16.3-2014 SEAM SLIPPAGE 93.5 Warp, 103.5 Fill ASTM D4034-92 TEAR STRENGTH: TONGUE TEAR 53 Warp, 22.7 Fill ASTM D2261-13

BLEACH RESISTANCE Yes, 10% Dilution

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass UFAC CLASS I Pass NFPA 260 Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS







Disclaimer: This product meets the Healthy Interior goals of the Safer Chemical Challenge according to the manufacturer Practice Greenhealth does not verify this information.

