

## DISTRIBUTORS OF LEATHER, VINYL, FABRIC & FOAM 4527 GLENWOOD ROAD • BROOKLYN, NY 11203

Phone: 718 941 3326 • Fax: 718 941 6115

Email: mark@dvcfabric.com



The super stain-resistant polyurethane™

This is an up-to-date spec sheet. This pattern never contained flame retardant, anti-bacterial, or anti-microbial additives

### PRODUCT SPECIFICATION SHEET

# Kelton

GENERAL SPECIFICATIONS

**SURFACE COMPOSITION** 100% Polyurethane SUBSTRATE COMPOSITION 100% Polyester WEIGHT 25.4 oz per linear yard WIDTH 54"

**THICKNESS** 1.40mm

ADDED PERFORMANCE SPECIFICATIONS

**HYDROLYSIS RESISTANCE** 10 weeks ISO 1419:1995 (Jungle Test)

STAIN RESISTANCE Yes

**COLORFASTNESS TO LIGHT** 200 Hours AATCC 16.3-2014, Option 3

**BLEACH RESISTANCE** Yes. 10% Dilution

COLD CRACK -20° F CFFA-6a-2007 **DENIM DYE TRANSFER RESISTANCE** Ford BN 112-09 Yes

**SULFIDE STAIN RESISTANCE** Yes

#### PHYSICAL PERFORMANCE SPECIFICATIONS

**ABRASION RESISTANCE** 250,000+ Double Rubs\* ASTM D4157-13 **BLOCKING** Rating 1 CFFA-4 **BREAKING STRENGTH** 129 Warp, 236 Fill ASTM D751-06 **COATING ADHESION** 4.42 Warp, 4.48 Fill ASTM D751-06 5 Dry, 5 Wet **CROCKING RESISTANCE AATCC 8-2016** 25,000+ **FLEX RESISTANCE** ASTM D2097-03 8.9 Warp, 12 Fill **TEAR STRENGTH: TONGUE TEAR** ASTM D751-06 83.9 Warp, 83.0 Fill **SEAM STRENGTH: TACK TEAR** ASTM D751-06 Warp 7.75% Stretch, 0.86% Set STRETCH AND SET SAE J855-2009

Fill 25.61% Stretch, 2.59% Set

\*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

#### FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass **UFAC CLASS I** Pass **NFPA 260** Pass

#### REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS LEAD / HEAVY METAL FREE PFC/PFOA FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS









Disclaimer: This product meets the Healthy Interior goals of the Safer Chemical Challenge according to the manufacturer Practice Greenhealth does not verify











