

Nassimi

PRODUCT SPECIFICATION SHEET



The faux leather that builds luxury into performance

Aspire

GENERAL SPECIFICATIONS SURFACE COMPOSITION SUBSTRATE COMPOSITION WEIGHT WIDTH THICKNESS COUNTRY OF ORIGIN	100% PVC (Phthalate Free) 100% Polyester 32 oz per linear yard 54" 1.20 mm Turkey	
ADDED PERFORMANCE SPECIFICATIONS	Yes	
COLORFASTNESS TO LIGHT	300 Hours	AATCC 16.3-2004, Option 3
BLEACH RESISTANCE	Yes, 10% Dilution	
COLD CRACK SULFIDE STAIN RESISTANCE	-20° F Yes	CFFA-6a-2007
PHYSICAL PERFORMANCE SPECIFICATIONS	105	
ABRASION RESISTANCE	250,000+ Double Rubs	ASTM D4157-10
BREAKING STRENGTH		ASTM D751-06
COATING ADHESION	7.35 Warp, 6.13 Fill	ASTM D751-06
CROCKING RESISTANCE	5 Dry, 5 Wet	AATCC 8-2007
FLEX RESISTANCE	25,000+	ASTM D2097-03
TEAR STRENGTH: TONGUE TEAR	11.2 Warp, 18.9 Fill	ASTM D2261-07
SEAM STRENGTH: TACK TEAR	60.7 Warp, 79.1 Fill	ASTM D751-06
ELONGATION	87.2% Warp, 76.8% Fill	
STRETCH AND SET	Warp Stretch 22%, Set 3.10%	SAE J855-2022
	Fill Stretch 22.11 %, Set3.63% Bias Stretch 20%, Set 2.94%	
	Dias Stretch 20%, Set 2.94%	

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

SS
SS
SS
SS

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS PHTHALATE FREE LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS



