

Cortez

General

| | |
|----------------------|-------------------------------------|
| Contents (Overall) | 85% PVC, 13% PES, 2% PU |
| Contents (Backing) | 100% Polyester |
| Fabric Type | Coated |
| Backing Type | Knit |
| Overall Weight | 26.5 oz/linear yard, 600 g/sm |
| Usable Width | 54" |
| Flame Retardants | No |
| Custom Color | 500 Meters |
| Production Lead Time | 15-20 days |
| Origin | Turkey |
| HTS Code | 5903.10.15 |
| Environmental | STANDARD 100 by OEKO-TEX®, Class IV |

| Specifications | Test Method | Result |
|---------------------------------------|-------------------------|--------------------------------------|
| Light Fastness (700 Hours) | AATCC 16.3-2014 | Grade 4/5 |
| Colorfastness: Chlorinated Pool Water | AATCC 105-1975 | Grade 5 |
| Colorfastness: Sea Water | AATCC 106-2013 | Grade 5 |
| Crocking: Dry | AATCC 8-2016 | Grade 5 |
| Crocking: Wet | AATCC 8-2016 | Grade 5 |
| Seam Slippage: Warp | ASTM D4034-1992 | 47.8 lbs |
| Seam Slippage: Weft | ASTM D4034-1992 | 68.3 lbs |
| Tear Strength: Warp | ASTM D2261-2013 | 4.0 lbs |
| Tear Strength: Weft | ASTM D2261-2013 | 9.0 lbs |
| Tensile Strength: Warp | ASTM D5034-2009 | 68.2 lbs |
| Tensile Strength: Weft | ASTM D5034-2009 | 89.4 lbs |
| Surface Abrasion- Wyzenbeek | ASTM D4157 | >150,000 (cotton duck) |
| Surface Abrasion- Martindale | ASTM D4966 | >100,000 (cotton duck) |
| Cold Crack (-15 F) | ASTM D751-2019 : 66-70 | No Cracking or Flaking |
| Hydrolysis (15 Weeks) | ISO 1419-2018, Method C | No Cracking, Peeling or Delamination |
| Antibacterial (Staph, K. pneumoniae) | AATCC 147-2011 | No Growth |
| Antifungal | ASTM G21-2013 | No Growth |
| Flame Retardancy | CAL TB 117-2013 | Pass |
| | NFPA 260 / UFAC | Class 1 |
| | IMO 2010 Part 8 | Pass |
| | FMVSS 302 | Pass |