

## Python

### General

Contents (Overall)	85% PVC, 13% PES, 2% PU
Contents (Backing)	100% Polyester
Fabric Type	Coated
Backing Type	Knit
Overall Weight	26.5 oz/linear yard, 600 g/sm
Usable Width	54"
Pattern Repeat	Vertical- 5 2/3" Horizontal- 6 1/8"
Flame Retardants	No
Custom Color	500 Meters
Production Lead Time	15-20 days
Origin	Turkey
HTS Code	5903.10.15
Environmental	STANDARD 100 by OEKO-TEX®, Class IV

Specifications	Test Method	Result
Light Fastness (300 Hours)	AATCC 16.3-2014	Grade 4/5
Crocking: Dry	AATCC 8-2016	Grade 5
Crocking: Wet	AATCC 8-2016	Grade 5
Adhesion: Warp	ASTM D751:46-49	3.4 lbs
Adhesion: Weft	ASTM D751:46-49	4.1 lbs
Seam Slippage: Warp	ASTM D4034-1992	53.8 lbs
Seam Slippage: Weft	ASTM D4034-1992	63.2 lbs
Tear Strength: Warp	ASTM D2261-2013	6.1 lbs
Tear Strength: Weft	ASTM D2261-2013	4.2 lbs
Tensile Strength: Warp	ASTM D5034-2009	59.5 lbs
Tensile Strength: Weft	ASTM D5034-2009	94.8 lbs
Surface Abrasion- Wyzenbeek	ASTM D4157-13	>150,000 (cotton duck)
Surface Abrasion- Martindale	ASTM D4966	>100,000 (cotton duck)
Cold Crack (-15 F)	ASTM D751-2019 : 66-70	No Cracking or Flaking
Hydrolysis (15 Weeks)	ISO 1419-2018, Method C	No Cracking, Peeling or Delamination
Flame Retardancy	CAL TB 117-2013	Pass
	NFPA 260 / UFAC	Class 1
	IMO 2010 Part 8	No
	FMVSS 302	No