

## Seville

### General

|                      |                                     |
|----------------------|-------------------------------------|
| Contents (Face)      | 100% Polyester                      |
| Contents (Backing)   | 100% Polyester                      |
| Fabric Type          | Warp Knit                           |
| Backing Type         | Brushed Knit                        |
| Overall Weight       | 16.4 oz/linear yard, 370 g/sm       |
| Usable Width         | 54"                                 |
| Performance Finish   | Water-Based Stain Repellency        |
| Dye Method           | Piece Dyed                          |
| Custom Color         | 500 Meters                          |
| Production Lead Time | 15-20 days                          |
| Origin               | Turkey                              |
| HTS Code             | 6005.37.00                          |
| Environmental        | STANDARD 100 by OEKO-TEX® , Class I |

| Specifications                     | Test Method              | Result                      |
|------------------------------------|--------------------------|-----------------------------|
| Light Fastness                     | AATCC 16.3:2012 Option 3 | Grade 4.5 @40 hours         |
| Crocking: Dry                      | AATCC 8:2016             | Grade 4.5                   |
| Crocking: Wet                      | AATCC 8:2016             | Grade 4.5                   |
| Seam Slippage: Warp                | ASTM D4034               | 120.1 lbs                   |
| Seam Slippage: Weft                | ASTM D4034               | 145.2 lbs                   |
| Seam Slippage: Opening @ 6mm: Warp | ASTM D4034               | 90.8 lbs                    |
| Seam Slippage: Opening @ 6mm: Weft | ASTM D4034               | 138.1 lbs                   |
| Tear Strength: Warp                | ASTM D2261:2013          | 11.9 lbs                    |
| Tear Strength: Weft                | ASTM D2261:2013          | 13.2 lbs                    |
| Tensile Strength: Warp             | ASTM D5034:2009          | 200.2 lbs                   |
| Tensile Strength: Weft             | ASTM D5034:2009          | 186.9 lbs                   |
| Surface Abrasion- Wyzenbeek        | ASTM D4157               | >102,000 (cotton duck)      |
| Brush Pilling                      | ASTM D3511               | Class 5                     |
| Flame Retardancy                   | CAL TB 117-2013          | Pass (without treatment)    |
|                                    | NFPA 260 / UFAC          | Class 1 (without treatment) |
|                                    | NFPA 701                 | Treatment required          |
|                                    | IMO 2010 Part 8          | Treatment required          |