






White




Linen



Ash



Cognac



Green Tea




Oxford




Black




Charcoal




Bark



Chestnut



Earth



Navy

Construction	Values	Test Method
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance	Minimum Values	Test Method
Grab Tensile	80 lbs./in. × 80 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. × 18 lbs./in. min.	ASTM D 751-06
Seam Strength	40 lbs./in. × 40 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	10% × 20%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	D-4; W-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-92
Hydrolysis Resistance	7 weeks	ASTM D 3690-02
UV Stability	150 hours	ASTM D 4329-05

Flammability		Environmental
California Technical Bulletin 117-2013, Sec. 1	Pass	1. No anti-microbial additives
IMO A.652(16)8.2	Pass	2. Does not contain PFAS, PFOA
NFPA 260	Pass	3. Prop 65 compliant
U.F.A.C. Class I	Pass	4. No chemical flame retardants, CA AB2998 compliant
		5. REACH, RoHS, and LEED compliant

Suitable Applications Commercial, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect products in commercial settings.