

Vestige

PRELIMINARY SPECIFICATION

+50% Bio-Attributed Polymer

COMMERCIAL SPECIFICATION

GENERAL		BACKING	
Weight	31 ± 10% OZ/YD LIN.	Descripción	Hi-Loft™ RPET
Width	54 inch	Weight	5.7 OZ/YD LIN. - ASTM D751
Topcoat	PERMABLOK® ADVANCED VINYL PROTECTION	Type	Polyester
Roll Length	30 yd		
Composition	PVC		
Gauge	43 ± 10% Mil		

SUSTAINABLE PRODUCT PROFILE			
ATTRIBUTES		COMPLIANCES	
Bio-Attributed Polymer		Backing Profile	
Phthalate Free	16 CFR PART 1307	Free of Flame Retardant Additives	AB-2998
SUSTAINABLE MANUFACTURING CERTIFICATIONS			
   			
 			
ADDITIONAL TESTS			
Tensile Strength Test - ASTM D751 / CFFA-17			
Lbf(Min.)	Warp	121	
	Fill	72	
Stretch Test - SAE J855 / CFFA-15			
%(Min.)	Warp	7.3	
	Fill	61.1	
Tear Strength - Tongue Method Test - ASTM D751 / CFFA-16b			
Lbf(Min.)	Warp	5.6	
	Fill	5.9	
Seam Strength Test - ASTM D751 / CFFA-14			
Lbf(Min.)	Warp	46	
	Fill	35	
Abrasion Resistant II Test - ASTM D4157 / CFFA-1a			
WYZENBEEK	100,000 Cycles	4.0	
Flex Resistance Test - ASTM D2097 / CFFA-10			
cycles	Warp	30.000 = Pass	
	Fill	30.000 = Pass	
Cold Crack Test			
CFFA-6a		-10°F	
FLAME RETARDANCY			
CFFA-4		No.1 - No Blocking ; No Adhesion	

FLAME RETARDANCY

US:NFPA 260 - Cover Fabric	Pass	US:UFAC Fabric Class 1	Pass
US:CAL TB 117	Pass		

This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

OTHER ATTRIBUTES

Anti Static	ASTM D257	Antistatic	Yes
healthcare	Yes		

MANUFACTURING CERTIFICATIONS



Note: The data correspond to minimum results of the statistical analysis. The information included in the specification is subject to change. The indicated data corresponding to the material's physical characteristics are results of test conducted under standard procedures and are subject to variation. We therefore recommend our customers to evaluate the material with regard to the specific requirements and application(s) before specifying. For additional information, please contact your sales representative. These terms and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

For a better experience, we recommend opening the file directly in a PDF viewer, and not in the browser.

Conscious of our impact. Designed for the long run. We are **ECOSENSE**[®] BY SPALDING